ESP-JETA
ESP Journal of Engineering & Technology Advancements
ISSN: 2583-2646 / Volume 5 Issue 3 July 2025 / Page No: 151-157
Paper Id: JETA-V5I3P120 / Doi: 10.56472/25832646/JETA-V5I3P120

Original Article

Pigment Dispersion Science in High-Speed Inkjet and Flexo Inks

Jigarkumar Bhailalbhai Patel
Independent Researcher, Eastern Michigan University, Ypsilanti, Michigan.

Received Date: 04 July 2025 Revised Date: 24 August 2025 Accepted Date: 19 September 2025

Abstract: *The physics of pigment dispersion is directly linked with the efficiency of the high-speed inkjet prints and flexographically (flexo) printing. The performance and desired chemical stability of pigments held in suspension by these inks become especially relevant as printing systems are strained to new speed systems, new specific resolutions, and to designs that are more sustainable. The article addresses physicochemical mechanisms, dispersion techniques, and applicable formulations of pigments in the mechanisms of stabilizing pigments in these new printing processes. The challenges of high throughput processes, the role of surface chemistry, particle continuum and medium interactions, as well as the role of dispersants, surfactants, and rheology modifiers are emphasized. An inkjet and flexo are compared in order to see the influence of formulation decisions on the print quality, nozzle performance, drying, and environmental impact. Improvements in the application of nano-politanisation and surface-modified pigments, and computational modeling of dispersion behaviour are also discussed. Recent literature is examined to provide experimental results in which formulation-performance correlations are illustrated. Lastly, sustainable approaches to pigment dispersion in the euphoria of sustainable chemistry, regulatory governance, and soaring prominence of bio-based and recyclable ink systems are taken into consideration.*

Keywords: *Pigment Dispersion, Inkjet Ink, Flexographic Ink, Surface Chemistry, Colloidal Stability.*

I. INTRODUCTION

The print technology has significantly changed within the last 20 years, as it was a traditional analog system and has now been replaced by high-throughput digital systems. Some of them include high-speed inkjet and flexographic printing, which have taken over in packaging and textiles, as well as in commercial printing. At the core of the performance of such technologies is the ink formulation, where pigment dispersion is a useful and characteristic defining determinant of the color strength, jetting reliability, adhesion to substrate, and long-term stability [1, 2].

Unlike dye-based inks, in which the dye is molecularly divided and dissolved in the vehicle, pigment-based inks exist in the vehicle as drums of small solid particles that must be suspended and stabilized in a complex formulation of solvents, resins, and other additives. Learning how to get a stable pigment distribution is therefore an interdisciplinary issue, and so the input of science of colloids and surface chemistry, as well as polymer physics and fluids, is required [3, 4]. The demands are even tougher in high-velocity systems: the nozzle diameters are tiny (say less than 50 microns), jetting velocities can be over 10 meters per second, and the drying times needed are of the order of milliseconds. Any polymerization or agglomeration of pigment may result in nozzle clogging and misfiring or undesired artifacts in print [5]. Also, the physicochemical environment in which pigments are employed is dramatically different regarding both inkjet and flexo systems. Inkjet inks are highly shear formulations of low viscosity to define a specific ejection of droplets; flexo inks are more viscoelastic and depend on the mechanical transfer of the ink with a pattern of plate roller. Every one of the systems puts its limits on the size distribution of the particles, zeta potential, surface treatment, and dispersant architecture [6]. Under these challenges and variations, this paper discusses the state-of-the-art of pigment dispersion science with respect to these two types of high-performance printing systems. This is because of dispersion mechanics to formulation impacts, where the future foreseen is intended to form a coherent narrative of the current practices and look into future innovations as well.

II. FUNDAMENTALS OF PIGMENT DISPERSION

Continuing on the relevance of pigment formulation presented in the section above, what needs to be learned is the physical and chemical foundations, which determine the process of pigment dispersion. A pigment dispersion is a suspension of a material (an insoluble material) in a liquid. There is a surplus of three large units (van der Waals attraction, electrostatic repulsion, and steric stabilization), which require a delicate balancing since they will contribute to guaranteeing stability. Without taking countermeasures against these forces, flocculation, agglomeration, or sedimentation takes place, the effects of which negatively affect the print quality [7, 8]. Electrostatic stabilization relies on the generation of a surface charge on pigment particles, often through pH manipulation or ionic surfactants. This repellent charge gives rise to a repulsive bilayer, which does not permit the nucleation of the particles. Although good, electrostatic stabilization is overly sensitive to ion strength and changes in pH, making it of limited use under complicated ink conditions. Alternatively, a powerful mechanism depending on polymer dispersants, applied to pigments, offers the steric stabilization mechanism, which is both insensitive to temperature and environmentally protective. These polymers entrap the long-term barriers in dispatcher entrapment, whereby they cannot approach each other due to the physical barriers (Entropic barriers) [9].

Pigment wetting comes in the first process of realizing stable dispersal in practice. This includes putting a liquid vehicle in place of air and hydrophobic pigments, surface impurities by expelling high shear stirring, and dispersing through adsorption of the dispersant as formulated in Figure 1. The process of deagglomeration, as a rule, is acquired through bead mills or ultrasonics and is feasible after the process of wetting. This process can be successful depending on the hardness of the pigments, the size of the primary facets, and even consideration of the chemical aspects of the chemical attraction between pigment and dispersant [10]. The surface pigmenting of surfaces is also important. Each of these functional groups can be adjusted in pigment surfaces by the manufacturers to fit them in a better manner to a specific dispersant or a specific vehicle. These restore dispersion stability and can also modify such optical properties as gloss or hue, or transparency [11]. This is the reason why such base matters as nowadays we go on to discuss the questions that are specific to how such inkjet and flexographic systems employ pigment dispersion strategies.



Figure 1: Stages of Pigment Dispersion: Wetting, Dispersing, and Stabilizing Pigment Particles for Uniform and Stable Color Distribution.

III. DISPERSION REQUIREMENTS IN HIGH-SPEED INKJET INKS

What has already been mentioned above is that pigment dispersions must fulfill, likely, one of the most demanding requirements imposed by inkjet printing. The geometric resolution of inkjet printheads is defined by nozzle sizes that are typically on the order of a few micrometers. This resolution is achieved through ejection mechanisms, which are commonly based on either piezoelectric or thermal actuation. To ensure smooth operation and prevent clogging, the dimensions of the pigment particles must be significantly smaller than the nozzle size. Typically, desired particles have narrow size distributions (PSD-0.2) and mean particle sizes smaller than 150 nm [12, 13]. The size requirement results in large-energetic milling particles, such as nano-bead milling and large surface-area dispersants that deposit on pigment surfaces. It is important that a dispersant is selected; low-molecular-weight dispersants may be so shear-averse that they become unstable, and long-chain dispersants may not only increase viscosity but are also disruptive in jetting [14].

Moreover, extreme thermal or mechanical stresses are exerted on inkjet inks. Such abrupt variations in acceleration and the subsequent pressure can bring about collisions of particles, and flocculation may be provoked in case dispersion is also borderline. The inks are thus typically scaled down to submicron length sizes and accelerated aging trials run to ascertain the stability under a given set of stressors [15]. The other aspect is the RF interaction between the pigment particles with the ink vehicle and print substrate. With regard to pigment-based inkjet inks, to achieve good wetting and adhesion of the ink on a wide variety of substrates, including coated papers to plastics, one must ensure that the dispersion is compatible with surfactants and binders that can modulate surface tension and drying rates. Poor dispersion may produce coffee-ring effects, banding, or bad-color densities [16]. There is an issue of environmental instability, too. Inkjet inks are many, and many modern inks have a water base due to their safety and other regulatory acts. Water as a solvent is, however, limited in its miscibility with several pigments and dispersants. Consequently, efficient water-soluble dispersants of amphiphilic structures are used to stabilize pigment in suspension and inhibit microbial growth [17]. This is hard on the inkjet printing requirements when compared to the requirements of flexographic inks, which is the focus of discussion in the following section.

IV. PIGMENT DISPERSION IN FLEXOGRAPHIC PRINTING INKS

Flexographic (flexo) printing relies on a highly divergent ink yield and inking techniques when compared to inkjet systems. Assisted inks employed are viscoelastic and are applied in the process by means of contacts (through the use of relief plates). Such variations influence patterns of pigment dispersion greatly. Pigment size requirements are somewhat looser than those used in inkjet printing, but well-dispersed pigment is required to assure print uniformities, reproducibility of colours, and keep plates clean when extended printing runs are necessary [18, 19]. Different sizes Formolicies Flexible inks are typically filled with much larger pigment, hundreds of nanometers, approximately 200 to 500 nm, which is many orders of magnitude in tolerances with ink jet systems. However, it cannot be used in non-uniform-sized particles to avoid mottling the substrate, screen clogging, and inefficient transfer. Flexible processes offer long, high-shear contact transfer of ink as opposed to inkjet systems, which generate shear forces on a micron level. Unless such shear is efficiently counteracted with strong dispersants, it is capable of aggregation of pigments [20]. Flexographic inks are also supposed to dry fast, especially those used on films, foils, or other nonporous materials. To obtain the required optical density of thin films, rapid solvent evaporation is necessary with a high pigment concentration. Excessive pigment loading can also enhance the likelihood of interparticle forces, hence the importance of efficient implementation of steric stabilization with the use of custom dispersants [21].

The other facing similarity in flexographic systems is different resin system compatibility. Dispersants have an essential role of first getting the pigments dissolved and must also constitute an integral part of an ink film, regardless of whether the ink is water, solvent, or UV curable. Pigments in UV curable systems require automatic distribution without negatively impacting the polymerisation kinetics [22]. Due to large-format presses and extended run times of flexographic printing, pigment dispersions must withstand some sedimentation and viscosity variations in lengthy operations. It is primarily possible to use thixotropic agents or rheology modifiers to keep the pigments suspended and provide their stable movement during printing [23]. Having talked about the inkjet and flexographic system peculiarities, we now ask ourselves what stabilisation of pigment dispersions on either platform is about, by way of surface chemistry.

The solid emphasis on the considerable differences in the technical features of flexographic inks and inkjet systems, and on the material composition of the ink and problematic factors of its functioning, makes it possible to better see the differences between the technologies with each other in terms of their attitude to pigments. These variations can be known to be summarised in the table below.

Table 1 : Comparative Overview of Pigment Dispersion Requirements in Inkjet vs Flexographic Inks

Parameter	Inkjet Inks	Flexographic Inks
Typical Pigment Size (D50)	< 150 nm	200–500 nm
Viscosity Range	1–10 mPa·s	50–500 mPa·s
Stabilization Mechanism	Electrosteric, often polymeric dispersants	Steric, sometimes ionic or amphiphilic
Sensitivity to Particle Agglomeration	Very High	Moderate
Film Thickness	Very Thin (~1–5 µm)	Thicker (~10–25 µm)
Common Solvent Systems	Water-based, glycol blends	Water, alcohols, UV-curable, or solvents
Printhead/Transfer Method	Non-contact, piezo or thermal jetting	Contact-based, via anilox roller
Key Stability Concerns	Nozzle clogging, sedimentation, and coffee-ring	Settling, print uniformity, and foam formation

Naturally, such a comparison underscores the significance of the mechanics and materials underlying each printing modality in the science of pigment dispersion.

V. SURFACE CHEMISTRY AND STABILIZATION MECHANISMS

The compatibility of pigments with pesticide behavior of the pigment dispersions of inkjet systems, as well as flexography inks, is largely determined through the surface chemistry. As is common knowledge, the stability of dispersions is directly related to the pigment particle, an interface they have with their environment, which is manipulated by the addition of surfactants, polymeric dispersants, and surface treatments [24, 25]. The third-party research proves that a significant fraction of printing inks using pigments tends to aggregate during dispersion in aqueous or polar solvents; such aggregation is helped by using surface modification techniques. Carboxylates, phosphonates, and polyethylene chains are functional groups that are covalently grafted or adsorbed to the pigment surface to increase hydrophilicity and promote the anchoring of dispersant. Such changes are also used to tune pigment-substrate interactions, to achieve enhanced adhesion and print sharpness [26]. Instead, dispersants are operative by anchoring their functional head groups to pigment surfaces and projecting solvated tails to the medium. Close contact between particles is prevented through the entropic barrier that the tails cause. The popularity of polymeric dispersants is explained by their emphasized anchoring and high steric hindrance. They can be customized previously with molecular weight, block type, and solubility to tailor towards specific ink types to the benefit [27].

Moreover, the value of an electrokinetic indicator of surface charge offers information on the stability of dispersion. In aqueous solutions, dispersants are chosen in a way that electrostatic repulsion forces are at least as large as the repulsive components of the zoo potential, which is approximately +30 mV or above. But in UV-curable systems as well as the high ionic strength solvent-based systems, steric mechanisms perform better than the electrostatic ones [28]. The combination of the pigments with the modified surfaces and designer dispersants determines the performance of the dispersion in the long run. Even thoroughly milled dispersions will quickly be destabilized under the influence of thermal, mechanical, or chemical stress unless surface chemistry is undertaken. This indicates the role of matching the chemical context of an ink formulation with pigment surface properties. In this light, the following section moves into formulation strategies and the way all the constituents of an ink-Links dispersion stability and print quality are achieved.



Figure 2 : Illustration of Key Stabilization Mechanisms in Surface Chemistry: Electrostatic, Steric, and Electrosteric Interactions Prevent Particle Aggregation and Enhance Dispersion Stability.

VI. FORMULATION STRATEGIES FOR STABLE AND HIGH-PERFORMANCE INKS

Ink formulation strategies were developed through a basic understanding of surface chemistry principles so that the pigment would be stable during storage, jetting/transfer, and drying/curing. Developing high-speed inks is a sensitive compromise of pigments, dispersants, solvents, binders, surfactants, and rheology modifiers, which are each individually chosen to balance each other and promote final use performance [29, 30]. Pigment loading is the point of departure. One wants to have higher pigment concentrations to achieve higher optical density, and this uphumps viscosity and risk of destabilization. In order to cope with that, high efficiency dispersants, which enable maximum pigment to be wetted with a minimum additive component, are used. Those dispersants should be compatible with the pigment surface and resin or binder system.

The choice of solvent is also a contributor to the stability of the dispersion. Water-based inks frequently incorporate co-solvents, including alcohols or glycols, to increase the solubility of other ingredients and to reduce evaporation, improving leveling and processing to a dry condition. The boiling point and polarity of the solvent used in solvent-based inks affect dispersant effects and how fast the pigment particles are immobilized within the drying film. Acrylics, polyurethanes, and polyesters of film formation have stopped these binders, which can enable easy attachment to the substrates. Such binders should be compatible with dispersants so that they do not phase-separate or flocculate pigment during drying. UV systems that use oligomeric binders should not cause HCl pigment to disperse or have an undesirable viscosity spike caused by storage effects. Some modifiers are added in order to control the contact between substrates: surfactants and wetting agents are placed on a substrate to make the surface tension free, allowing uniform ink deposit without beads forming. Even when concentrations of these agents are high enough, they can push dispersants off of pigment surfaces, leading to instability. Consequently, optimization must deal with the trade-off of wetting, foam, and dispersion. Application of rheology modifiers, especially in flexographic ink, also governs the computation of flow behavior. They are employed as stabilizers to ensure an ink remains stable during storage and also to ensure that it experiences low shear flow during printing. Associative thickeners and clays are widely used, provided they do not negatively interact with dispersants or pigment. Their formulation science-based strategies are corroborated by the experiments conducted to explicate their performance.

The system also has to involve an evaluation of the contribution of individual additives to an ink system, because the formulation strategies continue to alter. Rather than considering the contribution of each additive, the following table shows how the additives interact to form stable printable dispersions and the resultant consequences on ink and print properties.

Table 2 : Functional Roles of Ink Additives in Pigment Dispersion Systems

Additive Type	Primary Function in Dispersion	Secondary Effects
Dispersants	Anchoring on the pigment surface, a steric barrier	Affects pigment loading capacity; influences ink viscosity
Surfactants	Lowers surface tension; substrate wetting	May displace dispersants if overdosed; can affect foaming
Rheology Modifiers	Stabilize viscosity; resist sedimentation	Improve shelf-life; support flow under shear
Solvents	Pigment compatibility and flow	Control drying rate; affect ink substrate interaction
Binders/Resins	Film formation; adhesion to substrate	Interacts with dispersant; influences gloss and durability
pH Buffers/Modifiers	Adjust electrostatic repulsion	Prevent pigment flocculation in water-based systems

It is upon this logical inference of the workings of the additivity that the experimental analysis of the behaviour of the ink under conditions of operation was founded. The following section reports the experience of the practically executed performance of these formulations in inkjet and flexographic printers.

VII. EXPERIMENTAL INSIGHTS INTO DISPERSION BEHAVIOR

Theoretical bases of their formation remained unverified until experimental evidence was established, which in turn supported the validity of the proposed frameworks for their development and modes of formulation. Various types of pigment dispersions are used to gauge the determination of their quality of Set1 by including the computation of particle size, isolation of the zeta potential measurements, accelerated jetting measurements, ink transfer measurements, and print performance measurements. Sample variables and corresponding formulation parameters can be manipulated according to these studies to correspond with ink stability, print resolution, and nozzle under in situ operating conditions [1, 7, 14].

The criteria of evaluation at Inkjets experiments are usually nozzle stability and the homogeneity of droplets. The dispersions in pigment are subjected to faster jetting test cycles and nozzle clogging examination, satellite droplet formation, and consistent ejection. Higher results are found using high-performance polymeric dispersants applied to provide the stabilization conditions that ensure a small particle size distribution less than 150 nm after 30 days of ageing at higher temperatures (50°C) under constant jetting stress. The measurements of the zeta potential show that dispersions with a value above +30 mV and -30 mV could be stabilized under a variety of pH conditions, meaning a strong electrostatic or electrosteric force occurs [6, 13]. Laboratory analysis of print uniformity and dot gain is done in flexographic printing, as well as film formation on various substrates. Cross-experiments with varying dispersants have shown that non-ionic, amphiphilic block polymers and anionic surfactant systems exhibit the highest print density and saturated color with longer runs in the comparative experiments. These rolling measurements substantiate the fact that associative thickener inks with optimized and streamlined pigment dispersant percentages possess the required pseudoplastic flowability features and therefore, the equivalent distribution of ink is not dislodged during transportation, whereas the pigment falls [19, 21].

The surface rewrite of Porter pigments in the two systems also seems better in terms of comparative evaluation in the comparison to the untreated pigments. In general, pigments stabilized by carboxyl and polyethylene oxide groups have very high physical stability (sedimentation stability and compatibility with modern dispersants). These observations increase the homogeneity of the pigment distribution, quicker drying, and better rub-stability during printing [10, 24]. FTIR spectroscopy and rheometry carried out on UV-curable flexographic systems in real time demonstrate that disperse pigment does not have any effect on polymerase kinetics, demonstrating that full cure and adhesive strength are maintained without color kill. Moreover, ink jet ink massage experiments support that badly distilled inks are characterised by a high rate of clogging the filter (greater than 20 with a 0.45 µm membrane) and advise that the dispersions flow with ease, in which proponents propose that small particle contaminant is eliminated [12, 18]. These empirical observations support the pivotal situations of pigment surface treatment, dispersant selection, and formulation optimisation when the performance is to be consistent in all types of printing technologies, and therefore, they inform the upcoming trends in the field.

VIII. FUTURE TRENDS AND INNOVATIONS IN PIGMENT DISPERSION

The printing industry is developing, and pigment dispersion demands and the consequent innovations are developing along with it. Interest in new pigment technologies and dispersion technologies is driven by increasing demand for higher resolution and faster print rate, and environmentally friendly products. Among the most rewarding directions, there is the development of nano-dispersed pigments used in softeners that exhibit superior transparency, chroma, and stability because the size of the particles is less than 100 nm. Such fine dispersions would involve novel milling techniques and formulation of new dispersants capable of steric stabilization, which would proportionately not increase the viscosity. Contemporary research also uses machine-learning strategies to develop optimal dispersant architectures and milling equations that are pigment chemistry dependent, thereby reducing formulation trial and error times [8, 27]. Eco-friendly ink Production has become a major field of innovation. A visible trend is the use of bio-based dispersants, water-borne and low VOC solvents, equal in or surpassing the effectiveness of conventional petrochemical components, as well as biodegradable and non-toxic. Dispersants made of polysaccharides, lignin derivatives, and additives derived biologically are now under consideration with regard to pigment surface compatibility and binder resins [23, 30]. Also, the use of smart formulations becomes increasingly common now, i.e., formulations containing stimuli-responsive polymers which can undergo a conformational transformation or interaction modification in response to variations in pH, temperature, or shear. Such systems may be reversibly aggregating and dispersing and support self-healing rheology, adjustable drying rate, and longer shelf life [28]. In line with these advances, computational modeling and digital twin techniques are finding more use to aggregate pigment biofilms and forecast the stability of colloidal structures, and formulate formulations in silico before laboratory validation, shortening research and development timelines and increasing reproducibility in large-scale production.

The new additions of instrumentation are able to measure dispersion stability in real-time. We are allowing continuous control of quality at the moment of the ink by in-line particle-size analyzers, optical backscattering equipment, and microfluidic analyzers, which contributes to decreasing the rate of batch rejections and controlling the process better than usual. These developments represent the dry form of the ability to integrate materials science, computational chemistry, and process engineering, and the future of high-performance pigment dispersion in printing inks.

IX. CONCLUSION

Pigment dispersion science becomes the basis of the contemporary high-speed inkjet and flexographic printing. The development of stable, high-authority dispersions such as those described in this manuscript is complicated because of the surface chemistry, colloidal speeds, rheology, and formulation engineering. The varying components of dispersion behavior that encompass the shift of wetted, deaggregated, long-term storage stability, jetting of dispersions during printing will provide the quality of the end images, the efficiency of the system itself, as well as the working efficiency. The fact is that Inkjet inks also require a well-dispersed and stabilized suspension, but due to the existence of hard operating conditions as regards the nozzle diameter, shear stress, and the fast drying of the suspension. These are some extreme parameters that demand rigorous conditions on the sizes of particle distribution and the properties of the interface of particle to the mass that need to be taken care. Flexographic inks are less sensitive to particles, but when making them, a well-dispersed ink they need is high mechanical stress and not uniform requirements for interaction. This power is supreme in order to ensure a stable operation of the ink in the large volume flexographic production. Dispersants, hydrogels, and solvent systems should be limited to strictly those that have been optimized in order to both preserve pigment stability and be compatible with the entire ink formulation. Homogeneity in the long run will be achieved through a systematic method of excipient integration, which will minimize disruptive deviations at interfaces. Recent advances in the surface treatment of pigments, in the field of polymeric dispersants, nanotechnology, and real-time analytics and methods have significantly extended the horizons of formulation science. The technologies are able to sufficiently modulate the dispersion properties, but also gain information about the physicochemical mechanism. Additionally, the dynamics of sustainability, machine learning, and smart material creation introduce another initiative of the many opportunities to innovate. Establishing such tendencies will enable improved environmental performance, more efficient formulation development, and an adaptive ink system. Integrating the state-of-the-art science with the empirical test, this paper demonstrates that the pigment dispensation science might also be applied to formulate the subsequent generation of the inkjet and flexographic ink, which is expected to improve the image and print pace, along with raising sustainability in the printing industry.

X. REFERENCES

[1] Liu, S., Han, Z. and Luo, X., 2025. A comprehensive review on inkjet-printed intelligent food packaging materials: principle, ink formulation, functional inks, and potential applications. Food Frontiers.

[2] Qi, X., Luo, J., Liu, H., Fan, S., Ren, Z., Wang, P. and Wei, J., 2025. Flexible strain sensors based on printing technology: Conductive inks, substrates, printability, and applications. Materials, 18(9), p.2113.

[3] Yamanaka, T., Tarutani, N., Katagiri, K., Inumaru, K., Takeoka, Y. and Masui, T., 2022. High heat resistance of the structural coloration of colloidal arrays with inorganic black additives. ACS Applied Materials & Interfaces, 14(25), pp.29324–29330.

[4] Hakeim, O.A., Arafa, A.A., Zahran, M.K. and Abdou, L.A.W., 2014. UV-curable encapsulation of surface-modified organic pigments for inkjet printing of textiles. Colloids and Surfaces A: Physicochemical and Engineering Aspects, 447, pp.172–182.

[5] Liu, Y., Chen, Y., Yan, H., Chen, J., Chen, H., Li, S. and Zheng, G., 2025. High-stability electrohydrodynamic inkjet printing based on double closed-loop fuzzy control. Scientific Reports, 15(1), p.25794.

[6] Kuang, X., Rong, Q., Belal, S., Vu, T., López López, A.M., Wang, N. and Zhang, Y.S., 2023. Self-enhancing sono-inks enable deep-penetration acoustic volumetric printing. Science, 382(6675), pp.1148–1155.

[7] Gallant, B.M., Holzhey, P., Smith, J.A., Choudhary, S., Elmestekawy, K.A., Caprioglio, P. and Snaith, H.J., 2024. A green solvent enables precursor phase engineering of stable formamidinium lead triiodide perovskite solar cells. Nature Communications, 15(1),

p.10110.
[8] Korniejenko, K., Nykiel, M., Choinska, M., Jexembayeva, A., Konkanov, M. and Aruova, L., 2023. An overview of micro- and nano-dispersion additives for asphalt and bitumen for road construction. Buildings, 13(12), p.2948.
[9] Hakim, L., Deshmukh, R.K., Lee, Y.S. and Gaikwad, K.K., 2024. Edible ink for food printing and packaging applications: a review. Sustainable Food Technology, 2(4), pp.876–892.
[10] Wang, B., Li, Z., Wang, Y., Zhang, B., Lv, C., Bi, X. and Zhao, T., 2025. Eco-friendly dyeing of cotton fabrics with microbial pigments: Anionic modification for superior color, antibacterial, hydrophobic, and UV protection properties. Industrial Crops and Products, 223, p.120276.
[11] Sun, Y., Tong, Z., Yu, Y., Cheng, W., Li, Y., Zeng, S. and Yu, H., 2024. Solvent effects on carbohydrate transformation: insights into chemical pathway modulation. Green Chemistry, 26(12), pp.6900–6925.
[12] Wang, C., 2021. High-resolution direct ink writing of soft conductive materials. PhD. University of Illinois at Urbana-Champaign.
[13] Zhang, Y., Li, J., Song, X., Xu, C., Du, J., Miao, D. and Jiang, Y., 2025. Rheological behavior and storage stability study of liquid disperse dyes stabilized by polycarboxylate hyperdispersants. Journal of Molecular Liquids, p.128276.
[14] Lee, J.H., Kim, J.H., Hwang, K.T., Hwang, H.J. and Han, K.S., 2020. Formulation of a graft polymer-containing aqueous yellow ceramic ink for digital ink-jet printing. RSC Advances, 10(4), pp.2428–2436.
[15] Wang, P., Barnes, B., Huang, Z., Wang, Z., Zheng, M. and Wang, Y., 2021. Beyond color: The new carbon ink. Advanced Materials, 33(46), p.2005890.
[16] Jamaludin, L., Razak, R.A., Abdullah, M.M.A.B., Vizureanu, P., Bras, A., Imjai, T. and Yong, H.C., 2022. The suitability of photocatalyst precursor materials in geopolymer coating applications: A review. Coatings, 12(9), p.1348.
[17] Zhang, T., Xing, G., Chen, W. and Chen, L., 2020. Porous organic polymers: a promising platform for efficient photocatalysis. Materials Chemistry Frontiers, 4(2), pp.332–353.
[18] Muthamma, K., Gouda, B.M., Sunil, D., Kulkarni, S.D. and PJ, A., 2023. Water-based fluorescent flexo-ink for security applications. Chemical Papers, 77(7), pp.4033–4040.
[19] Roy, S., Vasudevan, R. and Chandrasekaran, S., 2025. A critical review of printed electronics and its application. Nanotechnology.
[20] Chan, K.F., Zaid, M.H.M., Mamat, M.S., Liza, S., Tanemura, M. and Yaakob, Y., 2021. Recent developments in carbon nanotube-reinforced ceramic matrix composites: A review on dispersion and densification techniques. Crystals, 11(5), p.457.
[21] Chen, Y.Y., Huang, K.T. and Huang, C.J., 2025. Polymerizable fatty acid surfactant: Encapsulation of organic pigments for excellent colloidal stability in aqueous solution and water-repellent property. Dyes and Pigments, 232, p.112488.
[22] Azani, M.R. and Hassanpour, A., 2024. UV-curable polymer nanocomposites: material selection, formulations, and recent advances. Journal of Composites Science, 8(11), p.441.
[23] Jalowy, L., Nemec, D. and Ilhan, O., 2025. Comparison of dispersing processes of bio-based and synthetic materials: A review. ChemEngineering, 9(2), p.36.
[24] Ahmed, K.A. and Ahmed, E.A., 2025. Fluorescent inks and their potential applications in textile printing. Journal of Industrial Textiles, 55, p.15280837241310890.
[25] Ahn, J., Lim, H., Ko, J. and Cho, J., 2024. Unlocking high-efficiency energy storage and conversion with biocompatible electrodes: the key role of interfacial interaction assembly and structural design. Energy Advances, 3(9), pp.2152–2174.
[26] Xie, Z., Wang, F., Li, J., Cui, N., Lu, L., Lu, H. and Qi, D., 2022. Nanoscale polymer encapsulated pigment hybrid latexes with high pigment content for binder-free pigment printing of cotton/polyester blend fabrics. Colloids and Surfaces A: Physicochemical and Engineering Aspects, 654, p.130107.
[27] Deng, Y., Liu, Y., Zhang, D. and Cao, Z., 2025. A hybrid gradient boosting model for predicting longitudinal dispersion coefficient in natural rivers. Water Resources Management, pp.1–21.
[28] Fatimi, A., Okoro, O.V., Podstawczyk, D., Siminska-Stanny, J. and Shavandi, A., 2022. Natural hydrogel-based bio-inks for 3D bioprinting in tissue engineering: a review. Gels, 8(3), p.179.
[29] Zhang, R. and Sun, T., 2024. Ink-based additive manufacturing for electrochemical applications. Heliyon, 10(12).
[30] Naik, N., Sunil, D., Rao, A. and Nayak, R., 2025. Biopolymer-based carbon conductive inks for printed electronics: a comprehensive review. Polymer Bulletin, pp.1–26.